

LIST OF CHEMICALS HYDRA-BOY

IMPORTANT NOTICE

The table „Chemical resistance of plastics“ was listed based on information from various raw material manufacturers. The values refer exclusively to laboratory tests with raw materials. Plastic parts made from them are often subject to influences that cannot be detected in laboratory tests (temperature, pressure, material stresses, exposure to chemical substances, design features, etc.). For these reasons, the values given can only serve as a guideline. In cases of doubt, we strongly recommend carrying out a test. No legal claim can be derived from this information, we exclude any warranty and liability. Chemical and mechanical resistance alone is not sufficient for assessing the serviceability of a product. In particular, the regulations for flammable liquids (explosion protection) must be taken into account.

COPYRIGHT

We would like to thank Bürkle GmbH for granting us the right to use this table. This table is published and maintained by Bürkle GmbH, D-79415 Bad Bellingen, Germany, as a referral guide. This copyright notice may not be removed. The table may be freely distributed and copied as long as the copyright notice remains intact.

LIST OF MATERIALS HYDRA-BOY

Tank:	PP	Suction hose:	PP, EVA
Sewage pump:	PP + GF20	Drain hose:	PP, EVA
Check valve:	PP	Floor nozzle:	PP
Screw connections:	PP	Suction tube:	PP
C-couplings:	PA6 + GF30	Suction head:	ABS

Version 3.11 (11.01.2021); Subject to technical changes, © Bürkle GmbH 2021.

rössle

Vacuum cleaners for fire departments

MEDIUM	FORMULA	CAS NO.	CONCEN TRATION	HAZARD INFORMATION	Thermoplastics													Fluoroelastics				Elastomers			Metals			Hastelloy C	REMARK		
					HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM	NBR	SI	AL	V2A			V4A	
Benzoic acid	C ₇ H ₆ O ₂	000065-85-0	saturated	Xn, Xi	1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1			
Benzoic acid	C ₇ H ₆ O ₂	000065-85-0	aqueous	Xn, Xi	1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1		
Benzoic acid sodium salt	-> see: Sodium benzoate																														
Benzoic acid aldehyde	-> see: Benzaldehyde																														
Benzoic acid benzyl ester	-> see: Benzyl benzoate																														
Benzoic acid chloride	-> see: Benzoyl chloride																														
Benzoic acid ethyl ester	C ₉ H ₁₀ O ₂	000093-89-0		Xn	2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Benzene	C ₆ H ₆	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1	0/0
Benzene-1,2-dicarboxylic acid	-> see: Phthalic acid																														
Benzene carboxylic acid	-> see: Benzoic acid																														
Benzene hexachloride (BHC)	-> see: Hexachlorocyclohexane																														
Benzenesulfonic acid	C ₆ H ₅ SO ₃	000098-11-3	saturated	C	1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0	1/0	0/0	
Benzoyl chloride	C ₇ H ₅ ClO	000098-88-4	100 %	C	0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)	0/0		
Benzyl acetate	C ₉ H ₁₀ O ₂	000140-11-4		Xn/Xi	1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1			
Benzyl alcohol	C ₇ H ₈ O	000100-51-6		Xn	3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1	3/3			
Benzyl benzoate	C ₁₄ H ₁₂ O ₂	000120-51-4		Xn	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)				
Benzylcarbinol	-> see: Phenylethanol																														
Benzyl chloride	C ₇ H ₇ Cl	000100-44-7	100 %	T/Xi	0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0		
Benzylether	-> see: Dibenzyl ether																														
Succinic acid	C ₄ H ₆ O ₄	000110-15-6	50 %	Xi	1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	1/1		
Succinic acid	C ₄ H ₆ O ₄	000110-15-6	saturated	Xi	1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	?		
Succinic acid diethyl ester	C ₈ H ₁₄ O ₄	000123-25-1		—	0/0	0/0	(2)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	0/0	(1)	(1)	(1)				
Bichromate sulphuric acid	-> see: Chromosulphuric acid																														
Beeswax	—	008012-89-3		—	1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)			
Beer	—			—	1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/1	1/1		
Bis(2-chloro-1-methylethyl)-ether	-> see: Dichloroisopropyl ether																														
Bis(2-ethylhexyl)-dipate	-> see: Dioctyladipate																														
Bis(2-ethylhexyl)-phthalate	-> see: Diisooctyl phthalate																														
Bis(2-ethylhexyl)-sebacate, sebacic acid bis(2-ethylhexyl)-ester	-> see: Dioctylsebacate																														
Bismuth chloride	BiCl ₃	007787-60-2		Xi	1/1	1/1	(3)	(2)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0		
Bismuth subnitrate	Bi ₂ O(HO) ₂ (NO ₃) ₄	001304-85-4		O, Xi	1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0			
Bisulphite	-> see: Sodium bisulphite																														
Bisulphite lye	NaHSO ₃	??		Xn	1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1	1/1		
Bisulphite lye, containing SO ₂	NaHSO ₃	??	saturated	Xn	1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1			
Bitter almond oil	C ₇ H ₆ O	090320-35-7		Xn	1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1		Main ingredient: Benzaldehyde		
Epsom salt	-> see: Magnesium sulphate																														
Bitumen	—	008052-42-4		—	0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)			
Hydrogen cyanide	HCN	000074-90-8	tech. pure	F+, T+	X	1/1	1/1	(3)	4/4	0/0	0/0	4/4	1/1	1/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	1/1	1/0	1/0		
Hydrogen cyanide	HCN	000074-90-8	aqueous	F+, T+	X	1/1	1/1	(3)	4/4	0/0	(4)	4/4	1/1	1/0	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	0/0	(1)	1/0	1/0	?	
Lead (II) acetate	C ₄ H ₆ PbO ₄	000301-04-2	aqueous	T, N	1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1	1/1
Lead (II) acetate	C ₄ H ₆ PbO ₄	000301-04-2		T, N	1/1	1/1	3/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1	1/1	
Lead(II) nitrate	Pb(NO ₃) ₂	010099-74-8	aqueous	O, T, N	1/1	1/1	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1		
Lead(II) nitrate	Pb(NO ₃) ₂	010099-74-8		O, T, N	1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1		
Lead nitrate	-> see: Lead (II) nitrate																														
Lead stearate	C ₃₆ H ₇₀ PbO ₄	001072-35-1		?	1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	No chemical effect expected due to low solubility		
Lead sulphate	PbSO ₄	007446-14-2		(T, N)	1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	0/0	(1)	(1)	(1)	No chemical effect expected due to low solubility	
Tetraethyllead	-> see: Tetraethyl lead																														
Lead sugar	-> see: Lead (II) acetate																														
Yellow prussiate of Potash	-> see: Potassium hexacyanoferrate(II)																														
Red prussiate of Potash	-> see: Potassium hexacyanoferrate(III)																														
Borax	-> see: Sodium borate																														
Boric acid	H ₃ BO ₃	010043-35-3	10 %	Xi	1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1		
Boric acid	H ₃ BO ₃	010043-35-3	aqueous	Xi	1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Spirits	-> see: Spirits																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

Chemical resistance of plastics
 (c) Bürkle GmbH 2021

					Thermoplastics										Fluoroelastics					Elastomers			Metals							
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE													V2A	V4A	Hastelloy C	REMARK									
					HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN					ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL
Brake fluid	—	—	—	?	1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Bromine	Br ₂	007726-95-6		T+, C	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	4/4	0/0	(4)	4/4	4/4	4/4
Bromine benzene	-> see: Bromobenzene																													
Bromobenzene	C ₆ H ₅ Br	000108-86-1		Xn	X	3/4	4/4	1/0	4/4	(2)	4/4	1/0	4/4	4/4	4/4	4/4	0/0	0/0	2/4	1/1	1/0	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	
Bromochloromethane	CH ₂ BrCl	000074-97-5	100 %	Xn		(4)	(4)	4/4	4/4	1/0	(4)	(3)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/0	(3)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0
Bromine vapours	Br ₂	007726-95-6		T		(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)	4/4
Bromine potassium	-> see: Potassium bromide																													
Bromomethane	CH ₃ Br	000074-83-9	tech. pure	T		3/0	4/4	1/0	(3)	0/0	0/0	1/0	4/4	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0
Bromoform	CHBr ₃	000075-25-2		T		4/4	4/4	4/4	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	0/0	0/0	2/3	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0	0/0
Bromopental fluoride	BrF ₅	007789-30-2		F, T, C		0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)	
Bromic acid	HBrO ₃	007789-31-3	concentrated	C		0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)	0/0	
Bromine trifluoride	BrF ₃	007787-71-5		T, C		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromotrifluoromethane	CBBrF ₃	000075-63-8		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Bromine water	Br ₂ +H ₂ O	007726-95-6	saturated	T		4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	0/0
Hydrobromic acid	HBr	010035-10-6	40 %	C		1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0
Hydrobromic acid	HBr	010035-10-6	50 %	C		1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0
Hydrobromic acid	HBr	010035-10-6	diluted	C		1/1	1/1	4/4	4/4	3/0	4/4	4/4	1/1	4/4	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0
Butadiene, 1,3-	C ₄ H ₆	000106-99-0		F+, T	X	3/4	4/4	1/0	4/4	1/0	4/4	(2)	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	4/4
Butane	C ₄ H ₁₀	000106-97-8	tech. pure	F+	X	1/0	1/1	1/0	1/0	1/0	1/0	2/0	1/1	4/4	1/0	1/0	3/0	1/0	0/0	1/1	1/1	1/0	4/4	1/0	1/0	0/0	1/1	(1)	(1)	1/1
Butanal	-> see: Butyraldehyde																													
Butanediol	-> see: Butylene glycol																													
Butanedioic acid	-> see: Succinic acid																													
Butanol	C ₄ H ₁₀ O	000071-36-3	techn. pure	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	0/0	
Butanol, secondary	-> see: Butyl alcohol, secondary																													
Butanol, tertiary	-> see: Butyl alcohol, tertiary																													
Butanol-2	-> see: Butyl alcohol, secondary																													
Butanone	-> see: Methyl ethyl ketone																													
Butanoic acid	-> see: Butyric acid																													
Butanetriol	C ₄ H ₁₀ O ₃	—	100 %	—		(4)	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	3/3	4/4	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	Isomer not specified in the source
Butene	C ₄ H ₈	—	tech. pure	F+	X	4/4	0/0	1/0	(1)	1/0	0/0	1/0	4/4	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/0	1/0	3/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0
Butenal, trans-2-	-> see: Crotonaldehyde																													
Butenedioic acid, cis-	-> see: Maleic acid																													
Butoxyethanol, 2-	-> see: Butyl glycol																													
Butter	—	—		—		1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	3/0	1/0	1/1	0/0	(1)	(1)	(1)	
Buttersäure	C ₄ H ₈ O ₂	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	1/1
Butyric acid ethyl ester	-> see: Ethyl butyrate																													
Butyl acetate	-> see: Acetic acid butyl ester																													
Butyl acrylate	C ₇ H ₁₂ O ₂	000141-32-2	100 %	Xi	X	1/2	2/3	2/0	4/4	1/3	2/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/0
Butyl alcohol	-> see: Butanol																													
Butyl alcohol, secondary	C ₄ H ₁₀ O	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)	
Butyl alcohol, tertiary	C ₄ H ₁₀ O	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)	
Butylamine	C ₄ H ₁₁ N	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0
Butyl carbinol	-> see: Amyl alcohol, n-																													
Butyl cellosolve	-> see: Butyl glycol																													
Butylene	-> see: Butene																													
Butylen glycol	C ₄ H ₁₀ O ₂	—	tech. pure	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	0/0
Butyl ether	-> see: Dibutyl ether																													
Butyl ethylene	-> see: Hexene, 1-																													
Butyl glycol	C ₈ H ₁₈ O ₂	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	0/0
Butylphenol	C ₁₀ H ₁₄ O	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1
Para tertiary butylphenol	C ₁₁ H ₁₆ NO	000098-54-4	tech. pure	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1
Butyl stearate	-> see: Stearic acid butyl ester																													

Two values are given for each medium:
 left number = value at +20°C / right number = value at +50°C

				----- Thermoplastics -----														----- Fluoroplastics -----				----- Elastomers -----				----- Metals -----						
MEDIUM	FORMULA	CAS NO.	CONCEN TRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM	FPM /FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK	
Chloral hydrate	C ₂ H ₃ Cl ₃ O ₂	000302-17-0	tech. pure	T/Xi		3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	0/0	0/0	
Chloramine T	C ₂ H ₃ ClN ₃ O ₂	000127-65-1	diluted	Xi		1/0	1/0	4/4	1/0	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	0/0	Swimming pool disinfection	
Phenyl chloride	-> see: Chlorobenzene																															
Chlorobenzene	C ₆ H ₅ Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	(1/1) ¹⁾	(1/1) ¹⁾	1/1	¹⁾ Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.	
Chlorine bleach	-> see: Sodium hypochlorite																															
Bromochloromethane	-> see: Bromochloromethane																															
Chlorobutadiene	C ₄ H ₅ Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0			
Chlorobutadiene	-> see: Calcium chloride																															
Chlorodifluoromethane	CHClF ₂	000075-45-6		N, Xn		0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0			
Chlorine dioxide	ClO ₂	010049-04-4		E, T		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4			
Chlorododecane	-> see: Lauryl chloride																															
Chloroacetic acid	C ₂ H ₃ ClO ₂	000079-11-8	50 %	T, C		1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	1/4		
Chloroacetic acid	C ₂ H ₃ ClO ₂	000079-11-8		T, C		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4			
Ethyl monochloroacetate	-> see: Ethyl chloroacetate																															
Chloroethanoic acid methyl ester	-> see: Methyl chloroacetate																															
Chlorethane	C ₂ H ₅ Cl	000075-00-3		F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	(1/1L) ¹⁾	(1/1L) ¹⁾	0/0	¹⁾ Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.	
Chloroethanol	C ₂ H ₅ ClO	000107-07-3	tech. pure	T+		1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	1/0		
Chloroethyl alcohol, 2-	-> see: Chloroethanol																															
Chloroethylene	C ₂ H ₃ Cl	000075-01-4	tech. pure	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0		(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0	0/0		
Chlorofluoromethane	CH ₂ ClF	000593-70-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0				
Chlorine gas	Cl ₂	007782-50-5		T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0			
Chlorinated potassium	-> see: Potassium chloride																															
Chlorinated lime	[3 x CaCl(OCI) + Ca —		aqueous	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach	
Chlorinated lime	[3 x CaCl(OCI) + C ₂ —			O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach	
Chloromethane	CH ₃ Cl	000074-87-3	tech. pure	F+, T	X	3/0	2/0	4/4	(3)	0/0	0/0	1/0	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/0	1/0	1/1	4/4	4/4	4/4	0/0	4/4	(1/1L) ¹⁾	(1/1L) ¹⁾		¹⁾ Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.	
Chloromethyl	-> see: Chloromethane																															
Chloromethylbenzene	-> see: Benzyl chloride																															
Chloromethyloxirane	-> see: Epichlorohydrin																															
Chloronaphthalene, 1-	C ₁₀ H ₇ Cl	000090-13-1		Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0			
Nickel chloride	-> see: Nickel (II) chloride																															
Chloroform	CHCl ₃	000067-66-3	100 %	Xn		3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	(1/1) ¹⁾	(1/1) ¹⁾	1/1	¹⁾ Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.	
Chloroprene	-> see: Chlorobutadiene																															
Chloropentafluoroethane	C ₂ ClF ₅	000076-15-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0				
Chloropentane, 1-	-> see: Amyl chloride																															
Chlorophenyl methyl ketone, 4-	-> see: Chloroacetophenone, -p																															
Chloropropane, 2-	-> see: Isopropyl chloride																															
Chloropropylene, 3-	-> see: Allyl chloride																															
Chloric acid	HClO ₃	007790-93-4	1 %	(C)		0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	1/0	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	Thermoplastics														Fluoroplastics				Elastomers				Metals		REMARK	
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A		V4A
Chloric acid	HClO ₃	007790-93-4	10 %	(O), C	1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	1/1	
Chloric acid	HClO ₃	007790-93-4	20 %	(O), C	3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	?	
Chlorosulfonic acid	ClHSO ₃	007790-94-5	tech. pure	C+	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	1/0	
Chlorotoluene	C ₇ H ₇ Cl	—		Xn	0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	1/1	Isomer not specified in the source
Chlorotoluene, alpha-	-> see: Benzyl chloride																													
Chlorine trifluoride	ClF ₃	007790-91-2		(O, T)	0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)		
Chlorotrifluoromethane	CClF ₃	000075-72-9		?	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0		
Chlorinated water	Cl ₂ x H ₂ O	007782-50-5		(T)	3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	3/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	0/0	
Hydrochloric acid gas	HCl	007647-01-0	anhydrous	T, C	1/1	0/0	4/4	(3)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	2/2L	2/2L	0/0	
Hydrochloric acid	-> see: Hydrogen acid																													
Hydronium chloride	-> see: Hydrochloric acid																													
Chlorozinc	-> see: Zinc chloride																													
Chromium (III) potassium sulphate dodecahydrate	-> see: Chrome alum																													
Chromium (VI) oxide	-> see: Chromic acid																													
Chrome alum	KCr(SO ₄) ₂ x 12H ₂ O	007788-99-0	saturated	Xn	1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	1/1	
Chromium salts	—	—	any	T/Xn	0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K		
Chromic acid	CrO ₃	001333-82-0	10 %	O, T, C, N	1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	1/1	
Chromic acid	CrO ₃	001333-82-0	20 %	O, T, C, N	0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	1/1	
Chromic acid	CrO ₃	001333-82-0	50 %	O, T, C, N	3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	1/1	
Chromic acid potassium salt	-> see: Potassium chromate																													
Chromosulphuric acid	CrO ₃ + H ₂ SO ₄	065272-71-1	concentrated	O, T, C, N	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	4/4	2/3	2/3	0/0	
Chromium trioxide	-> see: Chromic acid																													
2-Hydroxypropane-1,2,3-tricarboxylic acid	-> see: Citric acid																													
Citric acid tributyl ester	-> see: Tributyl citrate																													
Clophen A60	—	011096-82-5		Xn, N	0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	0/0	ppolychlorinated biphenyls, PCBs; Bayer
Cobalt (II) chloride	CoCl ₂	007646-79-9	aqueous	Xn	1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Cobalt dichloride	-> see: Cobalt (II) chloride																													
Colamine	-> see: Ethanolamine																													
Crotonaldehyde	C ₄ H ₆ O	004170-30-3	tech. pure	F, T	X	1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	0/0	
Cumol	-> see: Cumene																													
Cumene	C ₉ H ₁₂	000098-82-8		Xi	X	2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	0/0	
Curry	—	—		?	0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		could lead to discolouration
Ethyl cyanoacetate	-> see: Ethyl cyanoacetate																													
Cyanide	-> see: Potassium cyanide																													
Cyan potassium	-> see: Potassium cyanide																													
Cyannosodium	-> see: Sodium cyanide																													
Prussic acid	-> see: Hydrogen cyanide																													
Cyclanon	—	—		(Xn, Xi)	1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	0/0	Polyquaternary compounds, dyeing auxiliaries; BASF
Cyclohexane	C ₆ H ₁₂	000110-82-7		F	X	3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	0/0	
Cyclohexanol	C ₆ H ₁₂ O	000108-93-0	tech. pure	Xn	1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3	1/0	1/1	4/4	1/3	0/0	(1)	1/1	1/3	4/4	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Cyclohexanone	C ₆ H ₁₀ O	000108-94-1	tech. pure	Xn	X	1/3	3/4	1/0	4/4	(4)	3/4	1/0	2/4	4/4	4/4	4/4	4/4	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Cyclohexylmethane	-> see: Methylcyclohexane																													
Cymene, p-	C ₁₀ H ₁₄	000099-87-6		F, Xn/Xi	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	0/0	
Steam	H ₂ O	—	up to 150°C	?	4	4	4/4	0/0	0	0	(3)	(3)	0	0	0	0	0	0	0	1	0	1	3	4/4	0	(1)	1/1	1/1		
DDT (emulsion)	C ₁₄ H ₉ Cl ₅	000050-29-3		T	0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(3)	(3)	0/0	(2)	(2)	(2)	0/0		
Decahydronaphthalene	C ₁₀ H ₁₈	000091-17-8		Xn	1/3	3/4	1/0	4/4	3/0	4/4	1/0	3/4	4/4	4/4	1/2	3/0	3/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	(1)	(1)	0/0	
Decalin	-> see: Decahydronaphthalene																													
Decane	C ₁₀ H ₂₂	000124-18-5		Xn	X	0/0	0/0	(1)	(2)	(1)	(3)	1/1	(3)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	(1)		
Decanedioic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Decanedioic acid dibutyl ester	-> see: Dibutyl sebacate																													
Decanedioic acid diethyl ester	-> see: Diethyl sebacate																													
Dehydroacetic acid	C ₈ H ₆ O ₄	000520-45-6		Xn	0/0	0/0	(3)	(2)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(4)	(1)	(1)		
Densodrin W	—	—	aqueous	?	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	(1)	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0		Hydrophobing agent for leather, silicone derivative; BASF

MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	Thermoplastics											Fluoroplastics				Elastomers				Metals		REMARK				
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR		SI	AL	V2A	V4A
Glycerine	C ₃ H ₈ O ₃	000056-81-5	any	Xi	1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1		
Glycerol trinitrate	-> see: Nitroglycerin																													
Glycine	-> see: Aminoacetic acid																													
Glycol	-> see: Ethylene glycol																													
Glycol dinitrate	-> see: Nitroglycol																													
Glycolic acid	C ₂ H ₄ O ₃	000079-14-1	37 %	Xn	1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/3	1/1	
Glycolic acid	C ₂ H ₄ O ₃	000079-14-1	70 %	C, Xn	1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/1	
Glycocoll	-> see: Aminoacetic acid																													
Glycol chlorohydrin	-> see: Chloroethanol																													
Glysantin	—	—	—	Xn	1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	Antifreeze, basis glycol; BASF	
Glycerol triacetate	-> see: Triacetin																													
Firedamp	—	—	—	F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	mainly methane
Uric acid	C ₅ H ₄ N ₄ O ₃	000069-93-2	—	Xi	1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	0/0	
Urea	CH ₄ N ₂ O	000057-13-6	aqueous	Xi	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
Urea	CH ₄ N ₂ O	000057-13-6	—	Xi	1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/1	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
HD oil engine oil, aromatics-free	—	—	—	?	1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1	1/1		
Yeast	—	—	any	—	1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)		
Heating oil	—	—	—	Xn	3/3	3/4	1/0	3/3	1/0	2/3	1/1	1/3	3/4	1/2	1/1	3/3	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Helium	He	007440-59-7	—	—	0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1		
Hendecanol	-> see: Undecyl alcohol																													
Henkel-P3-solution	—	—	—	?	1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1	Cleaning agents	
Heptan, n-	C ₇ H ₁₆	000142-82-5	—	F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	0/0	
Heptanol, 1-	C ₇ H ₁₆ O	000111-70-6	—	Xn	0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)		
Heptanon	C ₇ H ₁₄ O	—	—	(Xn)	X	0/0	0/0	(3)	(4)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)	Isomer not specified in the source	
Heptanon-4	-> see: Dipropylketone																													
Heptyl alcohol	-> see: Heptanol, 1-																													
Hexachlorobenzene (HCB)	C ₆ Cl ₆	000118-74-1	—	T	0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0		
Hexachlorobutadiene (HCBd)	C ₄ Cl ₆	000087-68-3	—	T	0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexachlorocyclohexane (HCH)	C ₆ H ₆ Cl ₆	000319-84-6	—	T	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexadecanol	-> see: Cetyl alcohol																													
Hexadecanoic acid	-> see: Palmitic acid																													
Hexadecyl alcohol	-> see: Cetyl alcohol																													
Hexahydrobenzene	-> see: Cyclohexan																													
Hexahydrophenol	-> see: Cyclohexanol																													
Hexahydropridine	-> see: Piperidine																													
Hexahydrotoluene	-> see: Methylcyclohexane																													
Hexaldehyde	-> see: Hexanal																													
Hexamethylenetetramine	C ₆ H ₁₂ N ₄	000100-97-0	—	F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	0/0
Hexamine	-> see: Hexamethylenetetramine																													
Hexane, n-	C ₆ H ₁₄	000110-54-3	—	F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Hexanal	C ₆ H ₁₂ O	000066-25-1	—	F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Hexanedioic acid	-> see: Adipic acid																													
Hexanol, (1-)	C ₆ H ₁₄ O	000111-27-3	—	Xn	1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Hexanone-2	-> see: Methyl butyl ketone																													
Hexanetriol	C ₆ H ₁₄ O ₃	—	100 %	?	1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Hexen, 1-	C ₆ H ₁₂	000592-41-6	—	F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Hexylaldehyde	-> see: Hexanal																													
Hexyl alcohol	-> see: Hexanol, (1-)																													
Hexylene	-> see: Hexen, 1-																													
Staghorn salt	-> see: Ammonium carbonate																													
Wood alcohol	-> see: Methanol																													
Wood oil	—	008001-20-5	—	—	0/0	0/0	(1)	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)	(1)		
Wood tar oil	-> see: Creosote																													

MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	Thermoplastics											Fluoroplastics				Elastomers				Metals		REMARK								
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM	NBR		SI	AL	V2A	V4A	Hastelloy C			
Methanol	CH ₃ O	000067-56-1		F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0					
Methanoic acid	-> see: Formic acid																																	
Methenamine	-> see: Hexamethylenetetramine																																	
Methoxybenzene	-> see: Anisole																																	
Methoxybutanol	C ₆ H ₁₂ O ₂	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	!0	0/0	(1)	(1)	(1)	Isomer not specified in the source
Methoxyethanol	-> see: Methyl glycol																																	
Methoxyethyl acetate	-> see: Methyl glycol acetate																																	
Methoxyethyl oleate	C ₂₁ H ₄₀ O ₃	000111-10-4		?		1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	0/0	1/1	1/1	(1)	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)		Plasticiser		
Methoxypropanol	-> see: Propylene glycol methyl ether																																	
Methyl ethyl ether	C ₃ H ₈ O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)				
Methyl 2-hydroxybenzoate	-> see: Methyl salicylate																																	
Methyl 2-methyl propionate	-> see: Methyl methacrylate																																	
Methyl acetate	-> see: Acetic acid methyl ester																																	
Methacrolein	-> see: Crotonaldehyde																																	
Methyl acrylate	C ₄ H ₆ O ₂	000096-33-3		F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)				
Methylacrylic acid	-> see: Methacrylic acid																																	
Methyl alcohol	-> see: Methanol																																	
Methylamine, (Mono-)	CH ₃ N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	1/0	0/0			
Methylbenzene	C ₇ H ₈	000108-88-3		F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/3	4/4	0/0	1/1	1/1	1/1	1/1				
Methyl bromide	-> see: Bromomethane																																	
Methylbutanol	C ₆ H ₁₂ O	—		Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/3	0/0	(1)	1/1	1/1	3/0	2/2	3/3	0/0	(1)	(1)	(1)		Isomer not specified in the source		
Methylbutanol, 3-	-> see: Isoamyl alcohol																																	
Methylbutanone-2, 3-	-> see: Isopropyl methyl ketone																																	
Methyl butyl alcohol	-> see: Methylbutanol																																	
Methyl butyl ketone	C ₈ H ₁₆ O	000591-78-6		F, T	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)				
Methyl cellosolve	-> see: Methyl glycol																																	
Methyl chloroacetate	C ₂ H ₃ ClO ₂	000096-34-4	tech. pure	T/Xi	X	1/1	0/0	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	0/0	(1)	(1)	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0			
Methyl chloride	-> see: Chloromethane																																	
Methyl chloroform	-> see: Trichloroethane-1,1,1																																	
Methyl cyanide	-> see: Acetonitrile																																	
Methylcyclohexane	C ₇ H ₁₄	000108-87-2		F, Xn	X	3/0	3/0	(2)	(2)	1/0	(4)	(2)	3/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	(1)	4/4	(1)	4/4	0/0	1/1	1/1	1/1	0/0			
Methylcyclopentane	C ₆ H ₁₂	000096-37-7		F	X	0/0	0/0	(2)	(2)	1/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1				
Methyl dichloroacetate	C ₂ H ₂ Cl ₂ O ₂	000116-54-1		(Xn)		1/1	0/0	(3)	(4)		(4)	(3)	1/1	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/1	3/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0				
Methylene(dichloride)	-> see: Dichloromethane																																	
Methylene chlorobromide	-> see: Bromochloromethane																																	
Methyl ether	-> see: Dimethyl ether																																	
Methyl ethyl ketone (MEK)	C ₄ H ₈ O	000078-93-3		F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/2	1/3	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	3/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0				
Methyl formate	C ₂ H ₄ O ₂	000107-31-3		F+	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0			
Methyl glycol	C ₃ H ₈ O ₂	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0				
Methyl glycol acetate	C ₃ H ₁₀ O ₃	000110-49-6		T		0/0	0/0	1/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)				
Methyl isobutenyl ketone	-> see: Mesityl oxide																																	
Methyl isobutyl ketone(MIBK)	-> see: Isobutyl methyl ketone																																	
Methyl isopropyl ketone	-> see: Isopropyl methyl ketone																																	
Methyl methacrylate	C ₅ H ₈ O ₂	000080-62-6	100 %	F, Xi	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0				
Methyl methanoate	-> see: Methyl formate																																	
Methyl oleate	C ₁₉ H ₃₆ O ₂	000112-62-9		—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)				
Methyl oxirane	-> see: Propylene oxide																																	
Methylpent-4-en-2-one, 5-	-> see: Mesityl oxide																																	
Methylpentan-2-one, 4-	-> see: Isobutyl methyl ketone																																	
Methylphenol	-> see: Cresol (-mixtures)																																	
Methylphenyl ether	-> see: Anisole																																	
Methylphenyl ketone	-> see: Acetophenone																																	
Methylpropanol-1, 2-	-> see: Isobutanol																																	
Methylpropanol-2, 2-	-> see: Butyl alcohol, tertiary																																	

MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	Thermoplastics													Fluoroplastics				Elastomers			Metals		Hastelloy C	REMARK				
					HDPE	LDPE	PA	PC	PETG	PMMA	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL			V2A	V4A		
Tetrachloroethane	C ₂ H ₂ Cl ₄	—	tech. pure	T+		3/0	3/4	3/0	4/4	(4)	(4)	1/1	3/4	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0	0/0	0/0	Isomer not specified in the source
Tetrachloroethene	-> see: Perchloroethylene																															
Tetrachloroethylene	-> see: Perchloroethylene																															
Carbon tetrachloride (TETRA)	CCl ₄	000056-23-5		T		4/4	4/4	4/4	4/4	1/4	4/4	2/3	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	1/1	4/4	0/0	4/4	(1/1L) ¹⁾	(1/1L) ¹⁾	1/1	¹⁾ Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.	
Methane tetrachloride	-> see: Carbon tetrachloride																															
Tetrachlorotitanium	-> see: Titanium tetrachloride																															
Tetraethyl lead (TEL)	C ₈ H ₂₀ Pb	000078-00-2	techn. rein	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)	1/1		
Tetraethylorthosilicate	C ₈ H ₂₀ SiO ₄	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)			
Tetrafluoromethane	CF ₄	000075-73-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0				
Tetrahydro-1,4-oxazine	-> see: Morpholine																															
Tetrahydrofuran (THF)	C ₄ H ₈ O	000109-99-9		F, Xi	X	3/4	4/4	1/0	4/4	1/0	3/4	1/3	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	1/1		
Tetrahydrofurfuryl alcohol	C ₆ H ₁₀ O ₂	000097-99-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(2)	(1)	(1)			
Tetrahydronaphthalene	C ₁₀ H ₁₂	000119-64-2	tech. pure	Xi		3/4	4/4	1/0	4/4	1/0	(4)	1/0	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	1/0	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0		
Tetralin	-> see: Tetrahydronaphthalene																															
Tetramethylene oxide	-> see: Tetrahydrofuran																															
Tetraphosphorus decaoxide	-> see: Phosphorus pentoxide																															
Thiacyclopentadiene	-> see: Thiophene																															
Thiofuran	-> see: Thiophene																															
Thioglycolic acid	C ₂ H ₂ SO ₂	000068-11-1		T, C		0/0	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	(4)	0/0	3/4	0/0	1/1	0/0		
Thionyl chloride	Cl ₂ SO	007719-09-7	tech. pure	C		4/4	4/4	4/4	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	(3)	3/0	1/0	4/4	0/0	3/4	0/0	0/0	0/0		
Thiophene	C ₄ H ₄ S	000110-02-1		F, Xn	X	3/3	3/3	(2)	4/4	0/0	(4)	(2)	3/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	4/4	3/0	0/0	(1)	(1)	(1)	0/0		
Thymol	C ₁₀ H ₁₄ O	000089-83-8		C, Xn		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(3)	3/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	1/0	4/4	0/0	(1)	(1)	(1)			
Titanium chloride	-> see: Titanium tetrachloride																															
Titanium tetrachloride	TiCl ₄	007550-45-0		C		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0			
Toluene	-> see: Methylbenzene																															
Toluol	-> see: Methylbenzene																															
Toluenesulphone chloramide sodium, p-	-> see: Chloramine T																															
Tragacanth	—	009000-65-1		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1			
Transformer oil	—	—		?		1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/3	1/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)	0/0		
Grape sugar	-> see: Glucose																															
Triacetin	C ₉ H ₁₄ O ₆	000102-76-1		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)			
Tribromomethane	-> see: Bromoform																															
Tributyl citrate	C ₁₈ H ₃₂ O ₇	000077-94-1		—		1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)			
Tributyl phosphate (TBP)	C ₁₂ H ₂₇ PO ₄	000126-73-8	tech. pure	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1		
Trichloroacetaldehyde	C ₂ HCl ₃ O	000075-87-6	100 %	T/Xi		1/1	1/1	4/4	(3)	(4)	0/0	(3)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	0/0	(4)	3/0	(4)	4/4	0/0	4/4	0/0	0/0	0/0		
Trichloroacetaldehyde hydrate	-> see: Chloral hydrate																															
Trichloraldehyde hydrate	-> see: Chloral hydrate																															
Trichlorobenzene	C ₆ H ₃ Cl ₃	—	100 %	(Xn)		4/4	4/4	(3)	(3)	0/0	(4)	(2)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	(2)	(3)	(4)	(3)	4/4	0/0	(2)	0/0	0/0	0/0	Isomer not specified in the source	
Trichloroacetic acid (TCA)	C ₂ HCl ₃ O ₂	000076-03-9		C+		1/4	3/4	4/4	4/4	4/4	0/0	4/4	1/1	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	1/3	3/0L	2/0L	1/1		
Trichloroethane	C ₂ H ₃ Cl ₃	—		Xn		3/4	4/4	3/0	4/4	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	(1)	1/3	4/4	1/0	4/4	0/0	4/4	0/0	0/0	0/0	Isomer not specified in the source	
Trichloroethene	-> see: Trichloroethylene																															
Trichloroethylene (TRI)	C ₂ HCl ₃	000079-01-6	100 %	Xn		3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	(1/1L) ¹⁾	(1/1L) ¹⁾	1/0	¹⁾ Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.	
Trichlorofluoromethane	CCl ₃ F	000075-69-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	0/0		
Trichloromethane	-> siehe: Chloroform																															
Trichloromonofluoromethane	-> siehe: Trichlorfluormethan																															

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	Thermoplastics											Fluorooplastics				Elastomers				Metals		Hastelloy C	REMARK								
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR			SI	AL	V2A	V4A				
Trichlorophenol	C ₆ H ₃ Cl ₃ O	—		(Xn, Xi)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	0/0	0/0	0/0	Isomer not specified in the source
Trichlorophosphine	-> see: Phosphorus trichloride																																		
Trichlorophosphine oxide	-> see: Phosphorus oxychloride																																		
Trichlorophosphorus oxide	-> see: Phosphorus oxychloride																																		
Trichlorotrifluoroethane	C ₂ Cl ₃ F ₃	000076-13-1		?		0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0	0/0	0/0		
Triethanolamine (TEA)	C ₆ H ₁₅ NO ₃	000102-71-6	tech. pure	Xi		1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	(1)	0/0	0/0			
Triethylamine (TEA)	C ₆ H ₁₅ N	000121-44-8	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	(1)	0/0	0/0			
Triethylene glycol	-> see: Triglycol																																		
Triethylene glycol diacetate	-> see: Triglycol acetate																																		
Trifluorotrifluoroethane	C ₂ Cl ₃ F ₃	—	100 %	?		4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	4/4	1/0	3/4	4/4	3/3	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0	0/0	0/0	0/0	Isomer not specified in the source		
Triglycol	C ₈ H ₁₄ O ₄	000112-27-6		Xi		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	(1)	(1)	0/0	0/0			
Triglycol acetate	C ₁₀ H ₁₈ O ₆	000111-21-7		?		0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	(1)						
Trihydroxybenzoic acid, 3,4,5-	-> see: Gallic acid																																		
Trihydroxybenzene, 1,2,3-	-> see: Pyrogallol																																		
Trihydroxybutane	-> see: Butanetriol																																		
Trihydroxypurine, 2,6,8-	-> see: Uric acid																																		
Trihydroxytriethylamine	-> see: Triethanolamine																																		
Triiodomethane	-> see: Iodoform																																		
Triisopropylbenzene	C ₁₅ H ₂₄	000717-74-8		—		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)					
Tricresyl phosphate (TCF)	C ₂₁ H ₂₁ PO ₄	—	tech. pure	T/Xn, N		1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	Isomer not specified in the source	
Trimethylbenzene, 1,3,4-	-> see: Pseudocumene																																		
Trimethylpropane	C ₆ H ₁₄ O ₃	000077-99-6	aqueous	—		0/0	0/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)	(1)						
Trimethylpentane, 2,2,4-	-> see: Iso-octan																																		
Trisodium phosphate	Na ₃ PO ₄	007601-54-9		Xi		1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(4)	1/1	1/1						
Trisodium phosphate, tribasic	-> see: Sodium phosphate																																		
Trinitrophenol, 2,4,6-	-> see: Picric acid																																		
Trioctyl phosphate	C ₂₄ H ₅₄ PO ₄	000078-42-2	tech. pure	(Xn)		3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	0/0	0/0				
Tripfen	-> see: Hexachlorobutadiene																																		
Tripropylene glycol (TPG)	C ₉ H ₂₀ O ₄	024800-44-0		(—)		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)						
Tris(2-ethylhexyl) phosphate	-> see: Trioctyl phosphate																																		
Tris(hydroxyethyl)-amine	-> see: Triethanolamine																																		
Tris(hydroxymethyl)propane	-> see: Trimethylolpropane																																		
Tropic acid tropylester sulphate	-> see: Atropine sulphate																																		
Tung oil	-> see: Wood oil																																		
Turbine oil (mineral oil base)	?																																		
Superchloric acid	-> see: Perchloric acid																																		
Undecanol	-> see: Undecyl alcohol																																		
Undecyl alcohol	C ₁₁ H ₂₄ O	000112-42-5		Xi		1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)						
Urine	—																																		
Urotropine	-> see: Hexamethylenetetramine																																		
Vaseline	—	008009-03-8	tech. pure	(—)		3/4	2/3	1/0	1/0	1/0	0/0	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1			
Vaseline oil	—	008012-95-1	100 %	?		0/0	1/3	1/0	(2)	1/0	1/0	1/3	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	Paraffin oil		
Vaseline oil	—	008012-95-1		?		1/1	1/3	1/0	1/0	1/0	0/0	1/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	Paraffin oil		
Vinyl acetate	C ₄ H ₆ O ₂	000108-05-4	tech. pure	F	X	0/0	1/1	1/0	4/4	(3)	(4)	1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	1/0	3/0	3/3	0/0	(1)	(1)	(1)	(1)	0/0	0/0				
Vinylbenzene	-> see: Styrene																																		
Vinylcarbinol	-> see: Allyl alcohol																																		
Vinyl chloride	-> see: Chlorethylene																																		
Vinyl cyanide	-> see: Acrylonitrile																																		
Vinyl ethylene	-> see: Butadiene, 1,3-																																		
Vinylidene chloride	C ₂ H ₂ Cl ₂	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	0/0	0/0			
Vitamin C	C ₆ H ₈ O ₆	000050-81-7	liquid	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	(1)	(1)						
Wax alcohol	-> see: Paraffin oil																																		
Waxes	-> see: Paraffin oil																																		

MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	Thermoplastics														Fluoroplastics				Elastomers				Metals		REMARK		
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A		V4A	Hastelloy C
Sugar beet juice	—	—	—	—	1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)			
Sugar acid	—	—	saturated	(Xi)	1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0				
Sugar syrup	—	—	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Two-stroke oil	—	—	100 %	—	0/0	1/3	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1			

Resistance

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

0	no information available/no statement possible
1	very good resistance/suitable
2	good resistance/suitable
3	limited resistance
4	not resistant
K	no general information possible
L	Risk of pitting or stress corrosion cracking
()	Estimated value

Hazard preventions

E	explosive
O	oxidising
F	inflammatory
F+	extremely inflammable
T	toxic
T+	very toxic
C	caustic
Xn	harmful to health
Xi	irritant
N	environmentally hazardous

Name of materials

Thermoplastics

HDPE	High density polyethylene
LDPE	Low density polyethylene
PA	Polyamide (nylon)
PC	Polycarbonate
PETG	Polyethylene terephthalate glycol (co-polyester)
PMP	Polymethylpentene (TPX)
POM	Polyoxymethylene
PP	Polypropylene
PS	Polystyrene
PSU	Polysulfone
PVC	Polyvinyl chloride
SAN	Styrene acrylonitrile

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Halar)
ETFE	Ethylene tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon)
PTFE	FEP Polytetrafluoroethylene (Teflon)
PVDF	Polyvinylidene fluoride

Elastomers

EPDM	Ethylene propylene terpolymer rubber
FPM/FKM	Fluoropolymer (Viton)
NBR	Nitrile rubber
SI	Silicone rubber

Metals

Al	Aluminium
V2A	Stainless steel 1.4301 (AISI 304)
V4A	Stainless steel 1.4401 (AISI 316)
Hastelloy C	Nickel-chromium-molybdenum alloy